

Spezifikation/Normen: ISO/IEC 793, EN 50173, DIN VDE 0888, CCITT G. 651 (multi mode), G652.D (single mode)

	Gradientenindexfaser				Single mode
	Standard 50/125 μm (OM2+)	62,5/125 μm (OM1)	High Grade 50/125 μm (OM3)	50/125 μm (OM4)	E9/125 μm (OS2)

Geometrische Daten

Kerndurchmesser	50 $\pm$ 3 μm	62,5 $\pm$ 3 μm	50 $\pm$ 3 μm	50 $\pm$ 2,5 μm	
1310 nm					9,2 $\pm$ 0,4 μm
1550 nm					10,5 $\pm$ 1,0 μm
Manteldurchmesser	125 $\pm$ 3 μm	125 $\pm$ 3 μm	125 $\pm$ 3 μm	125 $\pm$ 1 μm	125 $\pm$ 1 μm
Durchmesser der Primärbeschichtung	245 $\pm$ 10 μm	245 $\pm$ 10 μm	245 $\pm$ 10 μm	245 $\pm$ 7 μm	245 $\pm$ 5 μm
Unrundheit des Kerns	< 6 %	< 6 %	< 6 %	< 5 %	
Unrundheit der Faser	< 2 %	< 2 %	< 2 %	< 1 %	
Exzentrizität zwischen Kern und Mantel	< 3 $\pm$ μm	< 3 $\pm$ μm	< 1,5 μm		

Optische Daten

Dämpfung					
850 nm	< 3,0 dB/km	< 3,5 dB/km	< 2,7 dB/km	< 2,5 dB/km	
1300 nm	< 1,0 dB/km	< 1,0 dB/km	< 0,7 dB/km	< 0,7 dB/km	
1310 nm					< 0,36 dB/km
1550 nm					< 0,22 dB/km
Dispersionsparameter					
1310 nm					< 3,5 ps/(nm x km)
1550 nm					< 18,0 ps/(nm x km)
Bandbreiten-Längenprodukt					
850 nm	> 500 MHz x km	> 200 MHz x km	> 1500 MHz x km	> 3500 MHz x km	
1300 nm	> 500 MHz x km	> 500 MHz x km	> 500 MHz x km	> 500 MHz x km	



	Gradientenindexfaser				Single mode
	Standard 50/125 µm (OM2+)	62,5/125 µm (OM1)	High Grade 50/125 µm (OM3)	50/125 µm (OM4)	E9/125 µm (OS2)
Linklänge 1 GBit/s					
850 nm	600 m	300 m	900 m		
1300 nm	600 m	550 m	500 m		
Linklänge 10 GBit/s					
850 nm			300 m	550 m	
1300 nm			300 m	300 m	
Brechungszahl					
850 nm	1,482	1,496	1,482	1,482	
1300 nm	1,477	1,491	1,477	1,477	1,468
1550 nm					1,468
Numerische Apertur	0,200 ± 0,02	0,275 ± 0,02	0,200 ± 0,015	0,200 ± 0,015	
Kabel- Grenzwellenlänge					< 1250 nm
Polarisationsmoden- Dispersions-Koeffizient (PMD)					< 0,5